CARE & MAINTENANCE

DAILY/WEEKLY MAINTENANCE:

- 1. Keep floor clean of dirt and debris with daily sweeping and vacuuming.
- 2. Occasional damp mopping using a mild cleaning agent (e.g., Simply Green) will maintain the beauty of the surface.
- 3. On rare occasions when the floor is extremely soiled, a cleaning agent made exclusively for rubber by Taski-Profy can be used. Follow the manufacturer's instructions on the cleaning agent. This product can be purchased from a janitorial supply dealer.
- 4. Rubberflex installed outdoors may be cleaned with a mild detergent, nylon bristle scrub brush and water. Ensure all soap residue is rinsed from Rubberflex before allowing to dry. Power washing using medium pressure nozzles may also be utilized for outdoor installations.

GENERAL PRECAUTIONS:

- 1. Care should be exercised when moving/relocating equipment over Rubberflex Flooring installations so as to prevent damage to the new floor
- 2. Do not scrub or strip fully adhered floors until at least 4 or 5 days after installation so that the Rubberflex flooring will have become well-seated in the adhesive.
- 3. The use of pads, wide casters/rollers, furniture/equipment cups, may prevent excessive indentation.
- 4. When moving heavy weight training machines over loose-laid Rubberflex rolls or tiles, plywood sheets should be placed over the floor area. Heavy machinery rolled or dragged over the flooring can create separation of double sided taped installations.

NOTE: The performance and guarantee of the products used in preparation, testing, installation and maintenance of Rubberflex, during and after installation, remain with the manufacturer of said product and not Centaur Floor Systems.

PRODUCT SPECIFICATIONS

1.01 DESCRIPTION

- A. Related Work Specified Under Other Sections:
- 1. Substructure Buildup
 - a. Asphalt for outdoor or indoor installations
 - b. Concrete for indoor installation.....Section 03300
- 2. Slab depression.
 - a. Depression shall be thickness of Rubberflex material specified 1/4", 3/8", or 1/2". Tolerance 1/8" in radius of 10'. Surface-steel troweled.
- 3. Membrane waterproofing and damp-proofing......Section 07100.
 - Concrete subfloors on or before grade shall be adequately waterproofed beneath and on the perimeter of the slab and on the earth side of below-grade walls
- 4. Thresholds: metals......Section 08700
- 5. Game standard insertsSection 11500

1.02 QUALITY ASSURANCE

- A. Supplier Qualifications: Supplier shall be an established firm, experienced in the field: Centaur or approved equal.
- B. Installer Qualifications:
 - 1. Flooring contractor shall be experienced in the flooring field and approved by the manufacturer.
 - 2. Flooring contractor shall be factory-approved and have completed at least three projects of similar magnitude and complexity.
 - 3. Submit three copies of manufacturer's recommendations for the correct preparation, finishing and testing of concrete (asphalt) subfloor surface to receive rubber sport surface.

1.03 SUBMITTALS

- A. Manufacturer's Product Data: Submit three copies of Physical Properties
- B. Samples: Submit three samples of Rubberflex Tuf-Roll or Tuf-Tile in thickness desired.
- C. Maintenance Literature: Submit three copies of Rubberflex maintenance instructions.



If you have any questions, feel free to contract us.

1.04 DELIVERY, STORAGE AND HANDLING

A. Delivery of material

- Material shall not be delivered or installed until all masonry, painting, plastering, tile work, marble and terrazzo work are completed, and all overhead mechanical work, lighting, backstops, scoreboards are installed. Room temperature shall be at least 55 degrees Fahrenheit and moisture content of concrete slab 8% or lower.
- 2. Area where materials are to be stored should be maintained at 55° Fahrenheit and under 50% relative humidity by the General Contractor

1.05 JOB CONDITIONS

- A. Do not install floor system until concrete has been cured thirty (30) days and the requirements in Paragraph 1.04 are obtained.
- B. After sport surface is installed and games lines painted, area is to be kept locked by General Contractor to allow curing time for paint and adhesive. No other trades are to be allowed on floor until it is accepted by owner or his agents.

1.06 GUARANTEE

- A. Guarantee shall not cover damage caused in whole or in part by casualty, ordinary wear and tear abuse, use for which material is not designed, faulty construction of the building, settlement of the building walls, failure of the other contractors to adhere to specifications, separation of the concrete slab and excessive dryness or excessive moisture from humidity, spillage, mechanical failure, migration through the slab or wall, or any other source.
- B. Centaur Floor Systems hereby warrants the Rubberflex Tuf-Tile or Tuf-Roll to be free of manufacturing defects for a period of five (5) years. This warranty is in lieu of all other warranties, expressed or implied, including, but not limited to, any warranty or merchantability or fitness for a particular purpose, and of any other obligations on the part of Centaur. In the event of breach of any warranty, the liability of Centaur, shall be limited to replacing Rubberflex material as supplied by Centaur and proven to be defective in manufacture, and shall not include any other damages, either direct or consequential.

2.01 MATERIALS

A. Description

- PRODUCTS

- Surface shall be rubber roll goods (Tuf-Roll) or Rubber Tiles (Tuf-Tile). Rolls shall be 4'-0" width x 30'-95' total length, determined by a combination of thickness
 and total roll weight. Materials shall be non-layered rubber product consisting of polymerically bound recycled rubber mixed with colored EPDM granules or
 pigmented SBR rubber. The colored rubber particles are homogeneously mixed throughout the entire tile once and have no chance of wearing away
- 2. The tiles shall be 36" x 36" total size with a variety of thicknesses available.

2.02 TECHNICAL DATA

A. Weight: Approx. 1.8 lbs/sq. ft. at 1/4" thickness

Approx. 2.5 lbs/sq. ft. at 3/8" thickness **Density:** 63 lbs/cu. ft. rolls; 60 lbs/cu. ft. tiles

Shore A Hardness ASTM Test: 55 Compression at 100 psi: 5 to 15

Recovery: 85 min.

Electric Conductivity: 1.1 x 10.2

Chemical Resistance: Unaffected by most acids and chlorine.

Abrasion Resistance: (2100 cycl): .5150 Coefficient of Friction: .057 dry; .072 wet

Compression Endurance: 10,000 cycles with 4 - 9 ton load

Acoustic Rating: Superior

Colors: Gray, Green, Red, Brown, Beige, Blue and Custom Blended Colors

New York State Fire Gas Toxicity Test: #09300-900216-4006

B. Adhesive

1. Rubberflex adhesive shall be approved by manufacturer, no substitutions. Adhesive shall be a single component POLYURETHANE adhesive over asphalt, wood or concrete. Use of any non-approved adhesive shall void warranty

3.01 INSPECTION

- A. Inspect concrete (or asphalt) subfloor for proper tolerance (see pt. B-Sec. 1.04-1) and dryness (see pt. 1 -Sec. 1.04-1) and report any discrepancies to General Contractor in writing.
- B. All work required to put concrete (asphalt) subfloor in acceptable condition shall be the responsibility of General Contractor
- C. Subfloor shall be broom cleaned by General Contractor.

3.02 INSTALLATION

- A. Rubberflex Tuf-Rolls
 - 1. Product should be unrolled and allowed to relax before cutting and fitting.
 - 2. Apply polyurethane adhesive according to manufacturer's directions on label. Use 1/8" notched trowel to spread adhesive.
 - 3. Unroll product into freshly applied adhesive. End seams will be single cut, edge seams overlapped, then snapped into place to insure tight seam.
 - 4. Roll the entire surface with steel roller to remove entrapped air. Wipe adhesive that oozes between seams with wood alcohol.
- See attached
- Perimeter Molding (Optional): Install a rubber base, anchored to walls with base cement.
- D. Clean up all unused materials and debris and remove same from the premises.

PART 3 - EXECUTION